

Turning insert, negative

	Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]									
						HC (CVD)									
						YBC103			YB6315			YBC152			
						Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			
		0,1	0,2	0,6	0,1	0,2	0,6	0,1	0,2	0,6					
P	Unalloyed steel	approx. 0,15 % C	annealed	125	1	520	420	280	500	400	270	500	400	270	
		approx. 0,45 % C	annealed	190	2	440	360	250	420	340	230	420	340	230	
		approx. 0,45 % C	tempered	250	3	350	300	220	330	280	200	330	280	200	
		approx. 0,75 % C	annealed	270	4	340	290	210	320	270	190	320	270	190	
		approx. 0,75 % C	tempered	300	5	300	260	190	280	240	170	280	240	170	
	Low-alloyed steel			annealed	180	6	420	320	200	400	300	180	400	300	180
				tempered	275	7	300	250	170	280	230	150	280	230	150
				tempered	300	8	280	240	170	260	220	150	260	220	150
				tempered	350	9	250	210	140	230	190	120	230	190	120
		High-alloyed steel and high-alloyed tool steel			annealed	200	10	380	310	210	360	290	190	360	290
			hardened and tempered	325	11	210	180	150	190	160	130	190	160	130	
M	Stainless steel	ferritic/martensitic	annealed	200	12										
			martensitic	tempered	240	13									
			austenitic	quench hardened	180	14									
			austenitic-ferritic		230	15									
K	Grey cast iron	perlitic/ferritic		180	16										
			perlitic (martensitic)		260	17									
	Cast iron with spheroidal graphite	ferritic		160	18										
			perlitic		250	19									
	Malleable cast iron	ferritic		130	20										
			perlitic		230	21									
N	Aluminium wrought alloys	cannot be hardened		60	22										
			hardenable	hardened	100	23									
	Cast aluminium alloys	$\leq 12\%$ Si, cannot be hardened		75	24										
			$\leq 12\%$ Si, hardenable	hardened	90	25									
			$> 12\%$ Si, cannot be hardened		130	26									
	Copper and copper alloys (bronze/brass)	machining steel, PB > 1%			110	27									
			CuZn, CuSnZn		90	28									
		CuSn, Pb-free copper, electrolytic copper		100	29										
S	Heat-resistant alloys	Fe-based alloys	annealed	200	30										
				hardened	280	31									
		Ni or Co base	annealed	250	32										
				hardened	350	33									
				cast	320	34									
	Titanium alloys	pure titanium		R _m 400	35										
		α and β alloys	hardened	R _m 1050	36										
H	Hardened steel		hardened and tempered	55 HRC	37										
			hardened and tempered	60 HRC	38										
	Hard cast iron		cast	400	39										
	Hardened cast iron		hardened and tempered	55 HRC	40										
X	Non-metallic materials	Thermoplastics			41										
		Thermosetting plastics			42										
		Plastic, glass-fibre reinforced GFRP			43										
		Plastic, carbon fibre reinforced CFRP			44										
		Graphite			45										
		Wood			46										

Note: The given cutting values are guide values, which were determined under ideal conditions.
 The values have to be adapted in individual cases.
 For examples of material for cutting tool groups view page D11.

Starting values for cutting speed v_c [m/min]																							
HC (CVD)																							
YBC203			YBC252			YBC352			YBM153			YBM253			YBD102			YB7315			YBD152		
Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]		
0,1	0,4	0,8	0,1	0,4	0,8	0,2	0,5	1,0	0,2	0,4	0,6	0,2	0,4	0,6	0,1	0,3	0,4	0,1	0,3	0,5	0,1	0,3	0,5
480	370	230	480	370	230	430	330	220															
400	310	190	400	310	190	350	270	180															
310	250	160	310	250	160	260	210	150															
300	240	150	300	240	150	250	200	140															
260	210	130	260	210	130	210	170	120															
380	290	170	380	290	170	320	240	150															
260	210	140	260	210	140	200	170	120															
240	200	140	240	200	140	180	160	120															
220	180	110	220	180	110	150	130	90															
310	250	170	310	250	170	220	180	130															
150	130	100	150	130	100	-	-	-															
									380	295	210	350	265	180									
									190	155	120	150	110	65									
									250	200	150	200	140	80									
									200	160	130	160	115	70									
															530	380	220	600	410	220	540	375	210
															240	200	150	330	240	150	280	210	140
															300	210	145	340	250	160	290	215	140
															220	150	105	260	190	120	210	155	100
															330	265	220	370	300	230	320	265	210
															230	155	100	280	200	120	230	165	100

- HC Coated carbide
- HT Uncoated carbide, primary component (TiC) or (TiN), cermet
- HW Uncoated carbide, primary component (WC)
- BL Cubic boron nitride with low BN content
- BH Cubic boron nitride with high BN content
- CN Si3N4 ceramic
- CM Mixed ceramic
- HC₁ Coated cermet
- BC CBN with coating
- CC Coated cutting ceramic
- CR Cutting ceramic, primary component aluminium oxide (Al₂O₃), reinforced
- DP Polycrystalline diamond

A

Turning

B

Milling

C

Drilling

D

Technical Information

E

Index



Turning insert, negative

Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]										
					HC (CVD)			HC (PVD)							
					YBD152C			YBG101			YBG102				
					Feed rate [mm]			Feed rate [mm]			Feed rate [mm]				
	0,1	0,3	0,5	0,1	0,3	0,6	0,1	0,3	0,6						
P Unalloyed steel	approx. 0,15 % C	annealed	125	1											
	approx. 0,45 % C	annealed	190	2											
	approx. 0,45 % C	tempered	250	3											
	approx. 0,75 % C	annealed	270	4											
	approx. 0,75 % C	tempered	300	5											
P Low-alloyed steel		annealed	180	6											
		tempered	275	7											
		tempered	300	8											
		tempered	350	9											
P High-alloyed steel and high-alloyed tool steel		annealed	200	10											
		hardened and tempered	325	11											
M Stainless steel	ferritic/martensitic	annealed	200	12							360	290	200		
	martensitic	tempered	240	13							180	150	110		
	austenitic	quench hardened	180	14							240	190	140		
	austenitic-ferritic		230	15							190	150	110		
K Grey cast iron	perlitic/ferritic		180	16	570	395	220								
	perlitic (martensitic)		260	17	310	230	150								
K Cast iron with spheroidal graphite	ferritic		160	18	310	230	150								
	perlitic		250	19	230	170	110								
K Malleable cast iron	ferritic		130	20	340	280	220								
	perlitic		230	21	250	180	110								
N Aluminium wrought alloys	cannot be hardened		60	22				2000	1200	-	2000	1200	-		
	hardenable	hardened	100	23				610	420	-	610	420	-		
	≤ 12% Si, cannot be hardened		75	24				550	300	-	550	300	-		
	≤ 12% Si, hardenable	hardened	90	25				360	190	-	360	190	-		
N Cast aluminium alloys	> 12% Si, cannot be hardened		130	26				320	170	-	320	170	-		
	machining steel, PB> 1%		110	27				730	350	-	730	350	-		
	CuZn, CuSnZn		90	28				370	330	-	370	330	-		
N Copper and copper alloys (bronze/brass)	CuSn, Pb-free copper, electrolytic copper		100	29				270	200	-	270	200	-		
	S Heat-resistant alloys	Fe-based alloys	annealed	200	30							65	45	-	
		hardened	280	31								60	40	-	
S Ni or Co bass	annealed	250	32								60	40	-		
	hardened	350	33								55	35	-		
	cast	320	34								55	35	-		
S Titanium alloys	pure titanium		R _m 400	35							100	60	-		
	α and β alloys	hardened	R _m 1050	36							80	40	-		
H Hardened steel		hardened and tempered	55 HRC	37											
		hardened and tempered	60 HRC	38											
	H Hard cast iron	cast	400	39											
H Hardened cast iron		hardened and tempered	55 HRC	40											
X Non-metallic materials	Thermoplastics			41											
	Thermosetting plastics			42											
	Plastic, glass-fibre reinforced GFRP			43											
	Plastic, carbon fibre reinforced CFRP			44											
	Graphite			45											
X Wood				46											

Note: The given cutting values are guide values, which were determined under ideal conditions. The values have to be adapted in individual cases. For examples of material for cutting tool groups view page D11.

Starting values for cutting speed v_c [m/min]																										
HC (PVD)															HC ₁			HT								
YBS103			YBG105			YB9320			YBG205			YPD201			YNG151C			YNG151			YNT251					
Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]					
0,1	0,3	0,6	0,1	0,3	0,6	0,1	0,3	0,6	0,1	0,3	0,6	0,1	0,3	0,6	0,1	0,2	0,4	0,1	0,2	0,4	0,1	0,2	0,4			
																	510	350	-	510	350	-	510	350	-	
																	430	270	-	430	270	-	430	270	-	
																	330	220	-	330	220	-	330	220	-	
																	320	200	-	320	200	-	320	200	-	
																	280	170	-	280	170	-	280	170	-	
																	400	240	-	400	240	-	400	240	-	
																	290	180	-	290	180	-	290	180	-	
																	240	170	-	240	170	-	240	170	-	
																	220	150	-	220	150	-	220	150	-	
																	340	220	-	340	220	-	340	220	-	
																	180	110	-	180	110	-	180	110	-	
	360	290	200	360	290	200	360	290	200	320	250	160	360	290	200											
	180	150	110	180	150	110	190	155	110	170	150	110	190	155	110											
	240	190	140	240	190	140	250	210	150	230	190	140	250	210	150											
	190	150	110	190	150	110	200	165	120	180	150	110	200	165	120											
																	430	365	280	430	365	280	430	365	280	
																	390	340	270	390	340	270	390	340	270	
																	360	300	220	360	300	220	360	300	220	
																	340	295	230	340	295	230	340	295	230	
																	310	260	190	310	260	190	310	260	190	
																	250	210	150	250	210	150	250	210	150	
	80	65	45	65	45	-	55	35	-	55	-	-	-	65	45											
	75	60	40	60	40	-	50	30	-	50	-	-	-	60	40											
	70	60	40	60	40	-	50	30	-	50	-	-	-	60	40											
	65	55	35	55	35	-	45	25	-	45	-	-	-	55	35											
	65	55	35	55	35	-	45	25	-	45	-	-	-	55	35											
	110	100	60	100	60	-	80	60	-	70	-	-	-	100	60											
	90	80	40	80	40	-	60	40	-	50	-	-	-	80	40											

- HC Coated carbide
- HT Uncoated carbide, primary component (TiC) or (TiN), cermet
- HW Uncoated carbide, primary component (WC)
- BL Cubic boron nitride with low BN content
- BH Cubic boron nitride with high BN content
- CN Si₃N₄ ceramic
- CM Mixed ceramic
- HC₁ Coated cermet
- BC CBN with coating
- CC Coated cutting ceramic
- CR Cutting ceramic, primary component aluminium oxide (Al₂O₃), reinforced
- DP Polycrystalline diamond

A
 Turning
B
 Milling
C
 Drilling
D
 Technical Information
E
 Index



Turning insert, negative

Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]									
					HW						BL			
					YD101			YD201			YCB112			
					Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			
	0,05	0,2	0,35	0,1	0,2	0,3	0,1	0,2	0,3					
P Unalloyed steel	approx. 0,15 % C	annealed	125	1										
	approx. 0,45 % C	annealed	190	2										
	approx. 0,45 % C	tempered	250	3										
	approx. 0,75 % C	annealed	270	4										
	approx. 0,75 % C	tempered	300	5										
P Low-alloyed steel		annealed	180	6										
		tempered	275	7										
		tempered	300	8										
		tempered	350	9										
High-alloyed steel and high-alloyed tool steel		annealed	200	10										
		hardened and tempered	325	11										
M Stainless steel	ferritic/martensitic	annealed	200	12										
	martensitic	tempered	240	13										
	austenitic	quench hardened	180	14										
	austenitic-ferritic		230	15										
K Grey cast iron	perlitic/ferritic		180	16										
	perlitic (martensitic)		260	17										
K Cast iron with spheroidal graphite	ferritic		160	18										
	perlitic		250	19										
K Malleable cast iron	ferritic		130	20										
	perlitic		230	21										
N Aluminium wrought alloys	cannot be hardened		60	22	1750	1200	800	1750	1200	800				
	hardenable	hardened	100	23	510	380	250	510	380	250				
	≤ 12% Si, cannot be hardened		75	24	460	320	175	460	320	175				
	≤ 12% Si, hardenable	hardened	90	25	300	205	110	300	205	110				
N Cast aluminium alloys	> 12% Si, cannot be hardened		130	26	270	185	100	270	185	100				
N Copper and copper alloys (bronze/brass)	machining steel, PB> 1%		110	27	610	410	205	610	410	205				
	CuZn, CuSnZn		90	28	310	250	195	310	250	195				
	CuSn, Pb-free copper, electrolytic copper		100	29	225	170	115	225	170	115				
S Heat-resistant alloys	Fe-based alloys	annealed	200	30										
		hardened	280	31										
	Ni or Co bass	annealed	250	32							180	160	140	
		hardened	350	33							160	140	120	
Titanium alloys	cast	320	34							120	100	80		
	pure titanium		R _m 400	35										
H Hardened steel	α and β alloys	hardened	R _m 1050	36										
		hardened and tempered	55 HRC	37							220	170	130	
H Hard cast iron		hardened and tempered	60 HRC	38							200	160	120	
		cast	400	39							200	150	100	
H Hardened cast iron		hardened and tempered	55 HRC	40							200	150	100	
X Non-metallic materials	Thermoplastics			41										
	Thermosetting plastics			42										
	Plastic, glass-fibre reinforced GFRP			43										
	Plastic, carbon fibre reinforced CFRP			44										
	Graphite			45										
	Wood			46										

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.
For examples of material for cutting tool groups view page D11.

A

Turning

B

Milling

C

Drilling

D

Technical Information

E

Index

Turning insert, negative

Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]																
					BC			BH			CM										
					YZB630C			YZB233			CA1000										
					Feed rate [mm]			Feed rate [mm]			Feed rate [mm]										
	0,1	0,3	0,5	0,3	0,9	1,5	0,1	0,6	1,5												
P Unalloyed steel	approx. 0,15 % C	annealed	125	1																	
	approx. 0,45 % C	annealed	190	2																	
	approx. 0,45 % C	tempered	250	3																	
	approx. 0,75 % C	annealed	270	4																	
	approx. 0,75 % C	tempered	300	5																	
P Low-alloyed steel		annealed	180	6																	
		tempered	275	7																	
		tempered	300	8																	
		tempered	350	9																	
P High-alloyed steel and high-alloyed tool steel		annealed	200	10																	
		hardened and tempered	325	11																	
M Stainless steel	ferritic/martensitic	annealed	200	12																	
	martensitic	tempered	240	13																	
	austenitic	quench hardened	180	14																	
	austenitic-ferritic		230	15																	
K Grey cast iron	perlitic/ferritic		180	16					1500	950	400										
	perlitic (martensitic)		260	17					1250	780	320										
K Cast iron with spheroidal graphite	ferritic		160	18					-	-	-										
	perlitic		250	19					500	300	100										
K Malleable cast iron	ferritic		130	20					-	-	-										
	perlitic		230	21					500	300	100										
N Aluminium wrought alloys	cannot be hardened		60	22																	
	hardenable	hardened	100	23																	
	Cast aluminium alloys	≤ 12% Si, cannot be hardened		75	24																
		≤ 12% Si, hardenable	hardened	90	25																
		> 12% Si, cannot be hardened		130	26																
Copper and copper alloys (bronze/brass)	machining steel, PB> 1%		110	27																	
	CuZn, CuSnZn		90	28																	
	CuSn, Pb-free copper, electrolytic copper		100	29																	
S Heat-resistant alloys	Fe-based alloys	annealed	200	30																	
		hardened	280	31																	
	Ni or Co bass	annealed	250	32																	
		hardened	350	33																	
		cast	320	34																	
Titanium alloys	pure titanium	R _m 400	35																		
	α and β alloys	hardened	R _m 1050	36																	
H Hardened steel		hardened and tempered	55 HRC	37	220	170	130					180	150	120							
		hardened and tempered	60 HRC	38	200	160	120					140	120	80							
	Hard cast iron	cast	400	39	200	150	100					80	60	40							
H Hardened cast iron		hardened and tempered	55 HRC	40	200	150	100					-	-	-							
X Non-metallic materials	Thermoplastics			41																	
	Thermosetting plastics			42																	
	Plastic, glass-fibre reinforced GFRP			43																	
	Plastic, carbon fibre reinforced CFRP			44																	
	Graphite			45																	
	Wood			46																	

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.
For examples of material for cutting tool groups view page D11.

A

Turning

B

Milling

C

Drilling

D

Technical Information

E

Index

Turning insert, positive

	Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]									
						HC (CVD)									
						YBC103			YB6315			YBC152			
						Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			
						0,1	0,2	0,4	0,1	0,2	0,4	0,1	0,2	0,4	
P	Unalloyed steel	approx. 0,15 % C	annealed	125	1	460	400	280	450	390	270	450	390	270	
		approx. 0,45 % C	annealed	190	2	390	340	240	380	330	230	380	330	230	
		approx. 0,45 % C	tempered	250	3	310	275	210	300	265	200	300	265	200	
		approx. 0,75 % C	annealed	270	4	300	265	200	290	255	190	290	255	190	
		approx. 0,75 % C	tempered	300	5	260	235	180	250	225	170	250	225	170	
	Low-alloyed steel			annealed	180	6	370	310	190	360	300	180	360	300	180
				tempered	275	7	260	220	160	250	210	150	250	210	150
				tempered	300	8	240	210	160	230	200	150	230	200	150
				tempered	350	9	210	180	130	200	170	120	200	170	120
		High-alloyed steel and high-alloyed tool steel			annealed	200	10	330	285	200	320	275	190	320	275
			hardened and tempered	325	11	170	160	140	160	150	130	160	150	130	
M	Stainless steel	ferritic/martensitic	annealed	200	12										
			martensitic	tempered	240	13									
			austenitic	quench hardened	180	14									
			austenitic-ferritic		230	15									
K	Grey cast iron	perlitic/ferritic		180	16										
			perlitic (martensitic)		260	17									
	Cast iron with spheroidal graphite	ferritic		160	18										
			perlitic		250	19									
	Malleable cast iron	ferritic		130	20										
			perlitic		230	21									
N	Aluminium wrought alloys	cannot be hardened		60	22										
			hardenable	hardened	100	23									
	Cast aluminium alloys	$\leq 12\%$ Si, cannot be hardened		75	24										
			$\leq 12\%$ Si, hardenable	hardened	90	25									
			$> 12\%$ Si, cannot be hardened		130	26									
	Copper and copper alloys (bronze/brass)	machining steel, PB > 1%		110	27										
			CuZn, CuSnZn		90	28									
		CuSn, Pb-free copper, electrolytic copper		100	29										
S	Heat-resistant alloys	Fe-based alloys	annealed	200	30										
				hardened	280	31									
		Ni or Co base	annealed	250	32										
				hardened	350	33									
				cast	320	34									
	Titanium alloys	pure titanium		R _m 400	35										
		α and β alloys	hardened	R _m 1050	36										
H	Hardened steel		hardened and tempered	55 HRC	37										
			hardened and tempered	60 HRC	38										
	Hard cast iron		cast	400	39										
	Hardened cast iron		hardened and tempered	55 HRC	40										
X	Non-metallic materials	Thermoplastics			41										
		Thermosetting plastics			42										
		Plastic, glass-fibre reinforced GFRP			43										
		Plastic, carbon fibre reinforced CFRP			44										
		Graphite			45										
		Wood			46										

Note: The given cutting values are guide values, which were determined under ideal conditions.
 The values have to be adapted in individual cases.
 For examples of material for cutting tool groups view page D11.

Starting values for cutting speed v_c [m/min]																							
HC (CVD)																							
YBC203			YBC252			YBC352			YBM153			YBM253			YBD102			YB7315			YBD152		
Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			Feed rate [mm]		
0,1	0,3	0,6	0,1	0,3	0,6	0,2	0,4	0,6	0,1	0,2	0,4	0,1	0,2	0,4	0,1	0,2	0,4	0,1	0,2	0,4	0,1	0,2	0,4
430	350	230	430	350	230	390	310	230															
360	295	190	360	295	190	315	250	190															
280	235	160	280	235	160	230	195	160															
270	225	150	270	225	150	220	185	150															
235	195	130	235	195	130	185	155	120															
340	270	170	340	270	170	290	225	150															
235	195	140	235	195	140	170	150	130															
220	180	140	220	180	140	150	140	130															
190	155	110	190	155	110	130	110	90															
280	230	170	280	230	170	180	160	140															
130	115	100	130	115	100	-	-	-															
									360	340	260	330	300	230									
									180	170	140	150	130	95									
									240	220	170	195	170	115									
									190	175	140	160	140	100									
															480	345	200	540	370	200	490	340	190
															220	180	135	300	220	135	250	190	130
															270	210	130	300	230	145	260	200	125
															200	150	95	230	180	110	190	140	90
															275	240	180	310	260	190	265	230	170
															190	145	85	230	170	100	190	140	90

- HC Coated carbide
- HT Uncoated carbide, primary component (TiC) or (TiN), cermet
- HW Uncoated carbide, primary component (WC)
- BL Cubic boron nitride with low BN content
- BH Cubic boron nitride with high BN content
- CN Si₃N₄ ceramic
- CM Mixed ceramic
- HC₁ Coated cermet
- BC CBN with coating
- CC Coated cutting ceramic
- CR Cutting ceramic, primary component aluminium oxide (Al₂O₃), reinforced
- DP Polycrystalline diamond



A	Turning
B	Milling
C	Drilling
D	Technical Information
E	Index

Turning insert, positive

Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]									
					HC (CVD)			HC (PVD)						
					YBD152C			YBG101			YBG102			
					Feed rate [mm]			Feed rate [mm]			Feed rate [mm]			
	0,1	0,2	0,4	0,1	0,2	0,4	0,1	0,2	0,4					
P Unalloyed steel Low-alloyed steel High-alloyed steel and high-alloyed tool steel	approx. 0,15 % C	annealed	125	1										
		approx. 0,45 % C	annealed	190	2									
		approx. 0,45 % C	tempered	250	3									
		approx. 0,75 % C	annealed	270	4									
		approx. 0,75 % C	tempered	300	5									
		annealed	180	6										
		tempered	275	7										
		tempered	300	8										
		tempered	350	9										
		annealed	200	10										
		hardened and tempered	325	11										
M Stainless steel	ferritic/martensitic	annealed	200	12						305	245	205		
	martensitic	tempered	240	13						150	125	100		
	austenitic	quench hardened	180	14						200	165	145		
	austenitic-ferritic		230	15						160	130	115		
K Grey cast iron Cast iron with spheroidal graphite Malleable cast iron	perlitic/ferritic		180	16	520	360	200							
		perlitic (martensitic)	260	17	280	210	135							
	ferritic		160	18	280	220	135							
		perlitic	250	19	210	160	100							
	ferritic		130	20	280	245	180							
		perlitic	230	21	210	160	100							
N Aluminium wrought alloys Cast aluminium alloys Copper and copper alloys (bronze/brass)	cannot be hardened		60	22				1800	880	-	1800	880	-	
	hardenable	hardened	100	23				540	380	-	540	380	-	
	$\leq 12\% \text{ Si}$, cannot be hardened		75	24				500	270	-	500	270	-	
		$\leq 12\% \text{ Si}$, hardenable	hardened	90	25				320	170	-	320	170	-
		$> 12\% \text{ Si}$, cannot be hardened		130	26				290	150	-	290	150	-
	machining steel, PB > 1%		110	27				660	320	-	660	320	-	
		CuZn, CuSnZn	90	28				330	300	-	330	300	-	
		CuSn, Pb-free copper, electrolytic copper	100	29				220	175	-	220	175	-	
S Heat-resistant alloys Titanium alloys	Fe-based alloys	annealed	200	30							60	45	-	
		hardened	280	31							55	40	-	
	Ni or Co bass	annealed	250	32							55	40	-	
		hardened	350	33							50	35	-	
		cast	320	34							50	35	-	
pure titanium		R _m 400	35							95	60	-		
	α and β alloys	hardened	R _m 1050	36							75	40	-	
H Hardened steel Hard cast iron Hardened cast iron		hardened and tempered	55 HRC	37										
		hardened and tempered	60 HRC	38										
		cast	400	39										
X Non-metallic materials		hardened and tempered	55 HRC	40										
	Thermoplastics			41										
	Thermosetting plastics			42										
	Plastic, glass-fibre reinforced GFRP			43										
	Plastic, carbon fibre reinforced CFRP			44										
Graphite			45											
Wood			46											

Note: The given cutting values are guide values, which were determined under ideal conditions. The values have to be adapted in individual cases. For examples of material for cutting tool groups view page D11.

Turning insert, positive

Material group	Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]								
					HW						BL		
					YD101			YD201			YCB112		
					Feed rate [mm]			Feed rate [mm]			Feed rate [mm]		
	0,1	0,2	0,3	0,1	0,2	0,3	0,1	0,2	0,3				
P Unalloyed steel	approx. 0,15 % C	annealed	125	1									
	approx. 0,45 % C	annealed	190	2									
	approx. 0,45 % C	tempered	250	3									
	approx. 0,75 % C	annealed	270	4									
	approx. 0,75 % C	tempered	300	5									
P Low-alloyed steel		annealed	180	6									
		tempered	275	7									
		tempered	300	8									
		tempered	350	9									
P High-alloyed steel and high-alloyed tool steel		annealed	200	10									
		hardened and tempered	325	11									
M Stainless steel	ferritic/martensitic	annealed	200	12									
	martensitic	tempered	240	13									
	austenitic	quench hardened	180	14									
	austenitic-ferritic		230	15									
K Grey cast iron	perlitic/ferritic		180	16									
	perlitic (martensitic)		260	17									
K Cast iron with spheroidal graphite	ferritic		160	18									
	perlitic		250	19									
C Malleable cast iron	ferritic		130	20									
	perlitic		230	21									
N Aluminium wrought alloys	cannot be hardened		60	22	1550	1050	700	1550	1050	700			
	hardenable	hardened	100	23	450	320	200	450	320	200			
	≤ 12% Si, cannot be hardened		75	24	400	270	150	400	270	150			
	≤ 12% Si, hardenable	hardened	90	25	250	170	95	250	170	95			
N Cast aluminium alloys	> 12% Si, cannot be hardened		130	26	230	150	85	230	150	85			
N Copper and copper alloys (bronze/brass)	machining steel, PB> 1%		110	27	550	370	170	550	370	170			
	CuZn, CuSnZn		90	28	260	210	160	260	210	160			
	CuSn, Pb-free copper, electrolytic copper		100	29	190	145	95	190	145	95			
S Heat-resistant alloys	Fe-based alloys	annealed	200	30	55	30	-	55	30	-	-	-	-
		hardened	280	31	55	25	-	55	25	-	-	-	-
	Ni or Co bass	annealed	250	32	45	25	-	45	25	-	180	160	140
		hardened	350	33	35	20	-	35	20	-	160	140	120
S Titanium alloys	cast	320	34	40	20	-	40	20	-	120	100	80	
	pure titanium	R _m 400	35	60	40	-	60	40	-	-	-	-	
S α and β alloys	hardened	R _m 1050	36	30	-	-	30	-	-	-	-	-	
H Hardened steel		hardened and tempered	55 HRC	37							220	170	130
		hardened and tempered	60 HRC	38							200	160	120
H Hard cast iron		cast	400	39							200	150	100
H Hardened cast iron		hardened and tempered	55 HRC	40							200	150	100
X Non-metallic materials		Thermoplastics		41									
		Thermosetting plastics		42									
		Plastic, glass-fibre reinforced GFRP		43									
		Plastic, carbon fibre reinforced CFRP		44									
		Graphite		45									
	Wood		46										

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.
For examples of material for cutting tool groups view page D11.

